1220
ELASTOMERIC BRUSH GRADE
SEAMSEAL

DESCRIPTION

Anvil 1220 Elastomeric Smooth Brush on Grade SeamSeal is a heavy bodied, flexible, elastomeric patching material for filling and patching cracks joints and seams on; masonry, stucco,concrete block, brick, stone, marble, wood, metal MH roofs and glass prior to applying finish. ***Anvil 1220 Elastomeric, Smooth, Brush on Grade SeamSeal*** provides excellent adhesion, long life, and is resistant to failure by expansion, contraction, or other joint movement. Fast drying and may be painted with latex or oil base paints. For use on interior or exterior surfaces.

SURFACE PREPARATION

Surface must be free of dirt, oil, grease, efflorescence, chalk, mildew, and loose material Any residual chalk left after pressure washing should be sealed with ***Anvil 230 or 231 Chalky Surface Conditioner.*** New Galvanized metal should be treated to remove mill oils. Ferrous metal should be free from rust and primed with ***Anvil 1606 Rust Inhibitive Primer Sealer.***

APPLICATION

Apply with brush or roller. Apply a generous first coat to seal entire area. For best results use polyester membrane to reinforce repair. Work membrane into wet sealant while smoothing to follow the contours of the area. Apply second coat of sealant to cover membrane and allow to dry before applying finish coat of paint.

LIMITATION OF LIABILITY

This product is manufactured to rigid control specifications. It is impossible to control the use and application. Therefore, the manufacturers sole liability is limited to replacing quantities of product proven to be defective. The manufacturer disclaims any liability for the cost of labor to repaint or any other use of the product.

TECHNICAL DATA

PRODUCT NUMBER: 1220 Elastomeric, Smooth Brush Grade, SeamSeal Caulking Compound

RESIN: Acrylic Latex

COLOR: White

GLOSS: Flat

SOLID CONTENT:
BY WEIGHT: 81.40%
BY VOLUME: 70.85%

RECOMMENDED COVERAGE:
100 Sq. Ft./Gal.

PIGMENT BY WEIGHT: 55.04%

VEHICLE BY WEIGHT: 44.96%

VISCOSITY: 120KU

WEIGHT PER GALLON: 13.26 lbs

FLASH POINT: N/A

DRYING TIME @ 70° F. 50% R.H:
Touch - 1/2 hour
Paint over - 1 to 2 hours
Full cure - 48 hours

Do not apply when rain, cold or nightfall is imminent. do not apply below 50 °F. Drying and cure time are influenced by ambient temperature and relative humidity.

THINNER/CLEANUP: Water
TINTING: Not Recommended
VOC: 45.6 grams/liter
AVAILABLE 1 & 5 GALLON PAILS

Revised 1-09 Supersedes all prior publications GRO

ANVIL PAINTS & COATINGS, INC. 1255 Starkey Road, Largo, Florida 33771 • FAX 727.535.1413
1.800.822.6776
www.anvilpaints.com